

CuZn37Pb2

CuZn37Pb2 | C35300

The CuZn37Pb2 alloy offers excellent machinability properties. Furthermore, its high copper content makes it suitable for both cold and hot working processes.

Comparable Standarts	
EN	UNS
CW606N	C35300

Chemical Composition %						
Cu	Zn	Ni	Sn	Fe	Pb	Al
61-62	rem	0.3 max	0.2 max	0.2 max	1.6-2.5	0.05 max

Physical Properties		
Density		(g/cm³)
Melting Point		[°C]
Thermal Conductivity		(W/mK)
Electrical Conductivity		%IACS
Modules of Elasticity		[GPa]
α @ 20°C		[10 ⁻⁶ /K]

Note: The specified conductivity applies to the soft condition only.

Cp specific heat

α thermal expansion coefficient

Fabrication Properties	
Machinability	good
Soft Soldering	excellent
Cold Formability	fair
Hot Formability	excellent
Gas shield arc welding	poor
Resistance welding	fair
Brazing	fair
Gas shield arc welding	poor

Typcial Uses

Watches and watch components, precision mechanical components, and milling plates, key production.

Corrosion Resistance

Machined brass is generally highly resistant to organic substances, as well as neutral or alkaline compounds. However, it is susceptible to stress corrosion cracking, particularly in an ammonia-containing atmosphere and under mechanical stress. Dezincification in warm, acidic waters must also be taken into account.

Mechanical Properties				
	Tensile Strength [MPa]	Yield Strangth [MPa]	Elongation A50 [%]	Hardness HV [-]

Other tempers are available upon request.

r = x * t (thickness t ≤ 0.5mm)

GW bend axis transverse to rolling direction. BW bend axis parallel to rolling direction.

